

The original recycled rubber impact sound insulation.
Since 2000.

A flat, resilient, recycled rubber underlayment to be used directly under most floor finishes, yielding exceptional results even under hard surface flooring, over concrete and wood joist construction



PERFORMANCE ATTRIBUTES

- Can thin-set tile and stone directly to the product per ASTM C627
- Compatible with most floor finishes
- Fast installation
- Available in 48" wide rolls and a variety of thicknesses
- Vapor barrier option available

- Crack isolation membrane protects ceramic, porcelain and stone tile from substrate cracks
- Rated extra heavy by the Tile Council of North America
- Passes VOC Washington State IAQ Test (ASTM D5116)
- Can contribute toward earning up to 9 LEED points

DIMENSIONS

- 15mm in 4' by 15' (1.2m by 4.6m) roll size
- Sheet weight: 2.2lb/ft²
- Standard Tolerances: Width: +3/4" - 0"; Length: +1% - 0"; Thickness: ±0.3mm

ACOUSTICS

Backed by over 400 independent lab and field tests, QTscu has been proven to provide the highest levels of IIC sound isolation in the industry. Contact us to access the test reports that meet your needs.

SAMPLE RATINGS: IIC 58, STC 61 with tile, 1 layer QTscu, Hambro D500 composite floor joist system, suspended ceiling (NGC 7005093, 5005044)



TECHNICAL DATA

The values shown represent current production based on standard QTscu specs and may vary per thickness. This material has a shelf life of 5 years from date of manufacture when protected from environmental extremes.

PROPERTY	TEST METHOD	TYPICAL RESULTS
Density	ASTM D297	0.85 g/cm ³ , min.
Thickness	ASTM D3676	15mm (0.59")
Tensile Strength	ASTM D412, Die C	110 psi, min.
Elongation	ASTM D412, Die C	30%, min.
Tear Strength	ASTM D624, Die C	20 ppi, min.
Compression @ 100 psi recovery	ASTM F36	15-25%, 85%, min.
Shore A Hardness	ASTM D2240	40
Flexibility	ASTM F147	1 factor, max.
Compression Set B, 25% Deflection, 158°/22 hrs	ASTM D395	50% max.
Coefficient of Friction	ASTM D1894	1.2

